



ARDEX WPM 155

Undertile PU Acrylic Hybrid Membrane

Modified Polyurethane Waterproof Membrane

Can be tiled over – excellent adhesion with ARDEX tile adhesives

Environmentally friendly – solvent free, suitable for confined areas

DISCLAIMER The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable New Zealand Standard, our instructions and recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

ARDEX WPM 155

Undertile PU Acrylic Hybrid Membrane Modified Polyurethane Waterproof Membrane

PRODUCT DESCRIPTION

Ardex WPM 155 (Undertile PU Acrylic Hybrid Membrane) developed for high performance under-tile waterproofing.

- Tough flexible film
- UV stable when left exposed
- Long shelf life
- Environmentally friendly – solvent free – suitable for confined areas
- Can be tiled over – good adhesion with Ardex tile adhesives
- Excellent adhesion to a wide range of substrates
- Fast drying

RANGE OF APPLICATIONS

For commercial and residential internal/external wet areas, balconies, decks and other areas that will be tiled or otherwise protected from regular foot traffic. Also suitable for undertile immersed conditions.

SUBSTRATES

Concrete

Cured for minimum 28 days, wet concrete should be allowed to dry thoroughly or sealed with one coat of Ardex WPM 300 at coverage rate of 3.0m² per litre.

Renderers and Screeds

Cured for min 7 days. Wet render should be allowed to dry thoroughly or sealed with one coat of Ardex WPM 300 at coverage rate of 3.0m² per litre and allowed to cure overnight.

Fibre cement sheets

Wet area grades only.

Plasterboard

Wet area grades only.

Plywood

Structural plywood (PAA branded) or marine grade.

PRIMERS

Ardex WPM 155 is suitable to use over Ardex WPM 300, Ardex WPM 350, Ardex WPM 270, Ardex WPM 265 or Ardex Multiprime.

APPLICATION

Ardex WPM 155 should be thoroughly mixed to a uniform mix and ensure the coating is applied evenly at recommended coverage rates. Mobile joints should be reinforced using Deckweb and the membrane must be lapped to intrusions such as waste outlets in accordance with the instructions. Apply Ardex WPM 155 by brush or roller. A medium nap (8-12mm pile) or 50mm long bristle paint brush is recommended.

COVERAGE

This will vary with the porosity of the substrates. Two coats are recommended to get optimum performance.

For floors

A dry film thickness of 1.0mm is required. A 20kg unit (15 Litres) will cover approximately 8m² (based on two coats).

For walls

A dry film thickness of 0.5mm is required. A 20kg unit (15 Litres) will cover approximately 16m².

DRYING TIME

Recoat time is 1-2 hours in between first and second coats. Drying time on flat surfaces under standard conditions is 4 hours. However, dry through time will be slower in areas where Ardex WPM 155 is applied over silicone bond breaker, or is reinforced. Make sure these areas are dry before tiling. In some cases, this can vary from 24 hours to 48 hours.

Full cure of the product is 3 days after application at 23°C. Drying times will vary depending on humidity, surface temperature and porosity of substrates.

PACKAGING

15L (20kg).

SHELF LIFE

12 months when stored in the original unopened packaging in a dry place at 23°C.

CLEANING

Wash hands, brushes, rollers with water while product is still fresh. For cured material, use mineral turpentine.

SAFETY PRECAUTIONS

All surfaces must be structurally sound, dry and free from all surface contaminants.

Do not use Ardex WPM 155 under the following conditions:

- Areas subject to negative hydrostatic pressure or rising damp.
- Wet substrates or green screeds/concrete – need to be sealed with one coat Ardex WPM 300 as described earlier.
- Surface temperature is below 10°C or greater than 35°C.

SAFETY DATA

Ardex WPM 155 is a non-hazardous and non-dangerous product. Wear protective clothing when handling. Wash off splashes with clean water. In case of eye contamination, rinse thoroughly with clean water. If irritation persists, seek medical advice.

ADDITIONAL INFORMATION IS LISTED IN THE MATERIAL SAFETY DATA SHEET.

QUALITY PRODUCT

Ardex WPM 155 is manufactured and tested to Ardex procedures which are maintained in accordance with Quality System Standard ISO 9001.

TECHNICAL PERFORMANCE DATA

Properties of Liquid material

Appearance	Blush Grey
------------	------------

Viscosity (6/20/25°C)

AS 1580:1990	30,000 cps
--------------	------------

Density (kg/L)

AS 4459:1999	1.36
--------------	------

Solids, by mass

AS1580:1992	65-68%
-------------	--------

Volume solids

AS1580-	53%
---------	-----

Properties of the Cured membrane

tensile Strength,

MPa AS 1145	1.2 MPa
-------------	---------

% Elongation	>350%
--------------	-------

Shore A Hardness	65-75
------------------	-------

Water Vapor Transmission

(AS4858/AStmE96)	1.2g/24hrs.m ²
------------------	---------------------------